



TECHNICAL DATA SHEET

5BG4.SILZN

ZINC BASED EPOXY-SILICON PRIMER

Creation date
Rev.

26/03/25
0

GENERAL INFORMATIONS		
Two-component epoxy-polyamide primer with a high zinc powder content, corrosion inhibitor for ferrous surfaces. It is suitable as a base for subsequent finishing with epoxy, synthetic polyurethane paints, etc.. It is used for applications on surfaces exposed to particularly corrosive atmospheres, for use in the chemical industry, oil industry, food industry, shipbuilding, construction and industrial bodywork.		
CHARACTERISTICS OF THE SUPPLY PRODUCT		
		NOTES
SPECIFIC WEIGHT	2,42 ± 0,1 Kg/L 2,10 ± 0,1 Kg/L (A+B)	
VISCOSITY	R4 20000 cP 20°C	Brookfield method
SPREAD RATING (75µm dry)	5-6 m ² /Kg	Theoretical
SOLID CONTENT	79 ± 1% (weight)	Theoretical A+B
AVAILABLE DYING	Zinc grey	
CATALYSIS	10% with HDR5.ZINCA (by weight)	

TECHNOLOGICAL CHARACTERISTICS AND RESISTANCE TESTS	
RESISTANCES	
ATMOSPHERIC AGENTS	Medium
NORMAL INDUSTRIAL ATMOSPHERE	Excellent
HEAVY INDUSTRIAL ATMOSPHERE	Excellent
MARINE ATMOSPHERE	Good
HIGH HUMIDITY ENVIRONMENTS	Good
ALTERNATING IMMERSION IN WATER	Excellent
CONTINUOUS IMMERSION IN WATER	Good
ORGANIC ACIDS	Medium
INORGANIC ACIDS AND ALKALIS	Good
ALIFATICALS	Very good
AROMATICS	Medium
ALCOHOLS	Good
ACID SALTS	Very good
ALCALINE SALTS	Very good
OILS AND FATS	Good



TECHNICAL DATA SHEET

5BG4.SILZN

ZINC BASED EPOXY-SILICON PRIMER

Creation date
Rev.

26/03/25
0

APPLICATION MODE	
SPRAY	Dilution 10-15% with epoxy thinner Nozzle Ø: 1.9- 2.2 mm Air pressure: 3-4 atm.
AIRLESS SPRAY	Nozzle Ø: 0,025÷0,030" compression ratio 30:1 Outlet pressure 130÷150 atm
<i>For spraying with airless equipment, since the product contains non-micronised fillers, the filters must be removed or replaced with others with a lower mesh count. It is necessary, when spraying, that the material taken from the gun comes from a low-pressure tank and under agitation, in order to prevent the zinc from sedimenting due to its high specific weight and its particular grain size.</i>	
HARDENING	
DUST FREE	15-20 min
TOUCH FREE	1 hours
DEEP DRY	24 hours
COMPLETE DRYING	7-10 days

OVERPAINTING
Overpaintable after 8 h and within 48 h (without sanding, after 48 h it will be necessary to roughen the surfaces by a slight mechanical roughening).
SURFACES PREPARATION
The ferrous substrate must be thoroughly degreased in accordance with norm. SSPC-SP1. <i>USE IN INLET:</i> White metal sandblasting SIS Sa3 (standard SSPC-SP5-82-NACE#1) up to an engraving depth of 50±25µm. Weld slag, oxides or any other impurities must be carefully removed. <i>OTHER USES:</i> Commercial sandblasting SIS Sa2 (SSPC-SP6-82-NACE#3) up to an engraving depth of 50±25µm.
ENVIRONMENTAL CONDITIONS
Drying problems can arise in environments with a temperature lower than 7 °C and relative humidity higher than 85 %; the application must in any case be carried out at a temperature of at least 3 °C above dew point, in a non-rainy or foggy atmosphere and on a dry and clean substrate.

Vivcolor s.r.l.



TECHNICAL DATA SHEET
5BG4.SILZN
ZINC BASED EPOXY-SILICON PRIMER

Creation date
Rev.

26/03/25
0

TOOLS CLEANINGS
Tools can be cleaned from the uncured product with the NITRO THINNER
STORAGE
In cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Its catalyst, in the same conditions as part A, at least 6.

The information on this data sheet is indicative and based on our knowledge derived from experience and experimentation and can in no way constitute a guarantee. The buyer/user decides independently the suitability of the product with respect to his own needs in the context of the specific field of use. Please refer to the relevant toxicological data sheet for safety information.